
Technical Information

STÜWADÄM

Suspension for the filling of drilling holes

The material consists of a powdered lime/cement/clay combination and is mixed with water without adding further components.



The recommended dosage for 1 m³ suspension is 700 kg STÜWADÄM and 700 kg water.
The achieved suspension density is 1.4.
STÜWADÄM is available in bags of 25 kg or big bags.

