

STÜWAPRESS

Ready to use sealing suspension for well

Stüwapress offers safe sealing with sufficient hold between well wall and permanent casing assembly after a short bonding time in order to separate different aquifers after drilling.

The recommended dosing for 1 m³ of suspension :

665 kg of STÜWAPRESS on 775 kg of water. The achieved density of suspension is 1,44. STÜWAPRESS is supplied in 25 kg bags or in big bags.



Density control by means of Hydrometer

The material comprises a combination of clay/ cement mixture, and can be mixed with water without adding any other components.



Mixing and injection:

e.g. with forced mixer & screw pump

